

Printed: 29.03.2013
Updated: 28.03.2013



EC - Declaration of Conformity

PAROC Pro Wired Mat 80

Issued in accordance with the Construction Products Directive (CPD) 89/106/EEC. This is to declare that this product conforms to the provisions of Annex ZA of EN 14303:2009 Thermal insulation products for building equipment and industrial installations – Factory made mineral wool (MW) products - Specification.

Certification Number	0809-CPD-0690 / VTT Expert Services Ltd, P.O. Box 1001, FI-02044 VTT, Finland, 18.12.2012
Designation Code	MW-EN 14303-T2-ST(+)+640-WS1-CL10
Short Description	Stone wool wired mat. Available also with stainless steel net; code W2 will be added after the product name.
Application	Fire and thermal insulation of cylindrical, conic and level surfaces.

Maximum Service Temperature		
Description	Value	In accordance with
Maximum Service Temperature (Declared), ST(+)+i	640 °C	EN 14706

Dimensions

Dimensions		Thickness
Width x Length		
Width 500/600/900/1000 mm, length 2000 - 8000 depending on thickness. mm	30 - 120 mm	
Standard EN 822	Standard EN 823	

Thickness Tolerance (Declared), T T2 / EN 14303

Fire Properties

Description	Value	In accordance with
Reaction to Fire, Euroclass	A1	EN 13501-1

Thermal Properties

Thermal Conductivity		
Description	Value	In accordance with
Thermal Conductivity (declared) in 0 °C, λ_0	0,035	EN 12667
Thermal Conductivity (declared) in 10 °C, λ_{10}	0,036	EN 12667
Thermal Conductivity (declared) in 50 °C, λ_{50}	0,040	EN 12667
Thermal Conductivity (declared) in 100 °C, λ_{100}	0,046	EN 12667
Thermal Conductivity (declared) in 200 °C, λ_{200}	0,064	EN 12667
Thermal Conductivity (declared) in 300 °C, λ_{300}	0,089	EN 12667
Thermal Conductivity (declared) in 400 °C, λ_{400}	0,121	EN 12667
Thermal Conductivity (declared) in 500 °C, λ_{500}	0,159	EN 12667
Thermal Conductivity (declared) in 600 °C, λ_{600}	0,204	EN 12667

Moisture Properties

Description	Value	In accordance with
Short Term Water Absorption (Declared), W_s, W_p	$\leq 1 \text{ kg/m}^2$	EN 1609

Trace Quantities of Water Soluble Ions		
Description	Value	In accordance with
Chloride Ions, Cl	< 10 ppm	EN 13468

Manufacturers

Paroc Oy Ab, Poikkitie 1, FI-53650 Lappeenranta

Paroc AB, SE-533 94 Hällekis

Paroc Polska Sp. z o.o., Ul. Gnieznienska 4, PL-62-240 Trzemeszno



Jim Lindström Business
Area Manager HVAC

Head Office: PAROC GROUP, P.O. Box 240 (Energiakuja 3), FI-00181 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab.

Paroc Group © 2013