



Technical Data Sheet EKAFOL Jacketing Form Parts from Isogenopak®

rigid PVC (Polyvinylchlorid) Material:

0,18 - 0,6 mm (PVC foil as a basic material) Foil thickness:

up to 2 mm (PVC sheets as a basic material)

gray, similarly RAL 7035 / 7047 Colour:

white, similarly RAL 9010 / 9016

black, similarly RAL 7021

On the insulation surface max. 50°C (DIN 4140) Temperature range:

Other qualities: Not UV-resistant

Information of the basic material:

Moisture resistance µ: app. 60'000 (DIN 52615)

Elasticity modulus: ca. 1800 N/mm2 (DIN EN ISO 527)

Emissivity: 97% (ISO 10292)

Weight: 1.37 g/cm3

Chemical resistance

Following the added papers of DIN 8061, 02/1984, Isogenopak® is resistant against chemical substances as follows:

Material	Temp. C°	Resistance	Material	Temp. C°	Resistance
Acetaldehyde up to 40 %, queous	20	+	Sodium chloride	40	++
Acetone, aqueous	20	-	Carbon monoxide, 100 %, gaseous	60	++
Aldehyde, 100 %	20	-	Methyl alcohol, every conc.	40	++
Aluminium salts	40	++	Mineral oils	60	++
Ammonia, aqueous	40	++	Sodium hydroxide, 60 %, aqueous	60	++
Ammonia, gaseous	60	++	Mercury	60	++
Benzene (pure aliphatic hydrocarbons)	60	++	Nitric acid, diluted, aqueous 30–50%	50	++
Benzene-benzole mix (fuel)	20	-	50-65%	20	++
Chlorine, gaseous (> 1 %), wet	20	+	98%	20	-
Chlorine, gaseous, dry	20	+	Hydrochlorid acid, aqueous up to 30 %	60	++
Hydrogen chloride, dry	60	++	Oxygen, gaseous	60	++
Iron salts, diluted solutions	40	++	Sulphur dioxide, gaseous (wet)	40	++
Iron salts, saturated solutions	60	++	Sulphur dioxide, gaseous (dry)	60	++
Acetic acid, 25-60 %	60	++	Sulphoric acid 40–80% 80–90% 96%		
Ethyl alcohol, solutions	40	++		60	++
Ethyl alcohol, 96 %	60	+		40	++
Glycerine	60	++		20	++
Potassium hydroxide	60	++	96%, fuming	60	+
solution, 50 %			5070, ruming	00	- F
Potassiferous salts	40	++	Carbon tetrachloride	20	+
			Hydrogen, gaseous	60	++

Key: not resistant

resistant under certain conditions

resistant

Page 1/2



















EKAFOL is a special rigid PVC film for cladding insulated pipes.

A dry, clean fitting is guaranteed. The inherent curl makes it the ideal material for quick and easy covering.

EKAFOL is self-extinguishing and has considerable resistance to acids, alkalis, salts, oil, petrol, aliphatic hydrocarbons and corrosive atmospheres. In addition, the material cannot corrode and is virtually impermeable to water vapour. It is unaffected by fresh and salt water and is impervious to gases, grease and oil. The chemical characteristics of **EKAFOL** are matched by equally good physical characteristics:

- high longitudinal and lateral tear resistance,
- high elasticity and shock resistance.

EKAFOL is very light:

one square meter, 0.350 mm thick weighs only about 500 g. This low weight and ease of stacking facilitates transportation and storage.

Physiologically harmless, **EKAFOL** has a smooth surface which guarantees a long-lasting elegant appearance. It requires no care or maintenance and also has very good anti-static characteristics. The material has considerable resistance to temperature changes and is stable from –20 °C up to +50 °C in indoor use. The thermal conductivity of **EKAFOL** is 0.16 W/mK.

Tips:

Color divergences between foil, form parts and adhesive tape are possible.

The information in this data sheet is based on our topical knowledge, experiences, as well as information of the manufacturer. The sheet does not contain a bill of sale or an assurance. No representation of warranty is made for specific product properties or concrete applications. All applicable current standards must be observed and followed. This document will supersede all previous data sheets.

Stand: 02.2010















