

Technical Data Sheet EKAPLAST – Jacketing Foil and Form Parts

Material:

Halogen-free thermoplast-foil
Fire class: B2 (DIN 4102)

Physical properties:

Colour: Grey, white, black, silver or in copper-optic
Environmental permanence: UV- and weather-resistant
Property: Free of halogens
Density: 1,32 g/cm³
Blow firmness: ≥ 250 kJ/m² (up to 500 µm foil thickness)
Tensile strength: ≥ 45 N/mm²
Elongation at rupture: ≥ 350 %
Elasticity module: ≥ 1500 N/mm²
Glaze point: ≈ 255 °C
Shrinkage: 10 min by 50°C = 0 %
10 min by 70°C ≤ 0,2 %
10 min by 140°C ≤ 10,0 %

Moisture resistance factor µ: Approx. 120 000
Sd-value: 42 mtr (foil-thickness 0,35mm)

Dimensions:

Material thickness: 0,15 ... 1,0 mm
Foil width: Only for Foils with curling effect: 1000 mm in grey, black and white
700 mm in copper- and silver optic
Tolerance: ≤ ± 5 %

Ranges of application:

Temperature range: As insulation-protect-jacketing
From -20 to +60 (°C) insulation outside temperature
Connection /Fixing EKAFIX rivets (in addition can be used a solvent or EKAFIX Butyl-tape)

Tips:

Color divergences between foil, form parts and adhesive tape are possible.
The information in this data sheet is based on our topical knowledge, experiences, as well as information of the manufacturer.
The sheet does not contain a bill of sale or an assurance. No representation of warranty is made for specific product properties or concrete applications. All applicable current standards must be observed and followed. This document will supersede all previous data sheets.

07/2012

