PAROC InVent 60 N3





Short Description Stone wool slab with black glass fiber non-woven tissue 60 g/m².

Application

Thermal and acoustical insulation of air conditioning machines etc.

Technical Properties Nominal Density 60 kg/m³ Fire Classification Euroclass: A1

Surface temperature of the facing must not exceed 80°C (temperature restriction determined in accordance with heat resistance adhesive). PAROC stone wool products are capable of withstanding high temperatures. The binder starts to evaporate when its temperature exceeds approximately 200°C. The insulating properties remain unchanged, but the compressive stress weakens. The softening temperature of stone wool products is over 1000°C.

Dimensions

Width x Length 600x1200 mm Other Dimensions Other dimensions subject to enquiry.

Thickness 25-100 mm

Packaging Pallet Package on Request Plastic foil Single Package Size 600x1200 mm Pallet Size 1200x1200 mm

Thermal Properties Thermal Conductivity in 10 °C, λ_{10}

Values announced by manufacturer.

Mechanical Properties Compressive Stress at 10 % deformation (Declared), CS(10), In accordance with (σ₁₀) ≥3 kPa

EN 826

0,037 W/mK



PAROC OY AB, P.O. Box 47 (Läkkisepäntie 23), FI-00621 Helsinki Finland, Tel. +358 46 876 8000, Fax +358 46 876 8002, www.paroc.com

The information in this data sheet represents the sole and comprehensive description of the condition of the product and its technical properties. However, the content of this data sheet does not mean granting a commercial guarantee. In so far as the product is used in an area of use which is not provided for in this data sheet, we cannot warrant its suitability for said area of use unless the suitability was expressly confirmed by us upon request. This data sheet replaces all previous ones. As a result of constant further development of our products we reserve the right to make alterations to data sheets. PAROC and red and white stripes are registered trade marks of Paroc Oy Ab. © Paroc Group 2011